

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): An aqueous dispersion type pressure-sensitive adhesive composition which consists essentially of a polyalkylene glycol having a weight-average molecular weight of from ~~100,000 to 3,000,000~~ 450,000 to 1,000,000 in an amount of from 0.5 to 15 parts by weight per 100 parts by weight, on a solid basis, of an acrylic pressure-sensitive adhesive composition of the aqueous dispersion type containing an acrylic polymer having a glass transition point of -20°C or lower and a weight-average molecular weight of at least 200,000, whereby the polyalkylene glycol is incorporated into the composition in the form of an aqueous solution after the polymerization of the acrylic polymer and

wherein the aqueous dispersion type pressure-sensitive adhesive composition has a property that when a pressure-sensitive adhesive product having a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is produced, the dewy or wet surface adhesive force thereof is 0.5 N/18 mm or more.

2. (withdrawn): An aqueous dispersion type pressure-sensitive adhesive composition which comprises at least one hydrophilic polymer selected from the group consisting of polyvinylpyrrolidone, poly(vinyl alcohol)s, and poly((meth)acrylic acid) in an amount of from 0.5 to 15 parts by weight per 100 parts by weight, on a solid basis, of an acrylic or rubber-based pressure-sensitive adhesive composition of the aqueous dispersion type.

3. (original): The aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 1, wherein the acrylic pressure-sensitive adhesive composition of the aqueous dispersion type comprises as a base polymer an acrylic polymer comprising a C₄₋₁₂ alkyl ester of (meth)acrylic acid as a main monomer component.

4. (withdrawn): The aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 2, wherein the acrylic pressure-sensitive adhesive composition of the aqueous dispersion type comprises as a base polymer an acrylic polymer comprising a C₄₋₁₂ alkyl ester of (meth)acrylic acid as a main monomer component.

5. (withdrawn): The aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 2, wherein the hydrophilic polymer has a weight-average molecular weight of from 500 to 5,000,000.

6. (withdrawn): The aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 4, wherein the hydrophilic polymer has a weight-average molecular weight of from 500 to 5,000,000.

7. (withdrawn): A pressure-sensitive adhesive product which comprises a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 1.

8. (withdrawn): A pressure-sensitive adhesive product which comprises a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 3.

9. (withdrawn): A pressure-sensitive adhesive product which comprises a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 2.

10. (withdrawn): A pressure-sensitive adhesive product which comprises a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 4.

11. (withdrawn): A pressure-sensitive adhesive product which comprises a pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition as claimed in Claim 5.

12. (withdrawn): The pressure-sensitive adhesive product as claimed in Claim 7, wherein the pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is disposed on at least one side of a porous base material.

13. (withdrawn): The pressure-sensitive adhesive product as claimed in Claim 8, wherein the pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is disposed on at least one side of a porous base material.

14. (withdrawn): The pressure-sensitive adhesive product as claimed in Claim 9, wherein the pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is disposed on at least one side of a porous base material.

15. (withdrawn): The pressure-sensitive adhesive product as claimed in Claim 10, wherein the pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is disposed on at least one side of a porous base material.

16. (withdrawn): The pressure-sensitive adhesive product as claimed in Claim 11, wherein the pressure-sensitive adhesive layer formed from the aqueous dispersion type pressure-sensitive adhesive composition is disposed on at least one side of a porous base material.